


(PACLD0001)
DRY TAC GTC 50/30



- Clear Gloss PET Film 30
- Adhesive DT-1
- Clear Gloss PET Film 50
- Adhesive V-1
- Silicone
- KW55

Facestocks

- Reference 1: Clear Gloss PET Film 30
Thickness (μ): 30
Grammage (gr/m²): 42
- Reference 2: Clear Gloss PET Film 50
Thickness (μ): 50
Grammage (gr/m²): 70

Liner

- Reference: KW55
Description:
Bleached kraft paper, coated on one side and treated on the backside
Thickness (μ): 58
Grammage (gr/m²): 55

Adhesives

- Reference 1: DT-1
- Reference 2: V-1
Characteristics:
Permanent adhesive acrylic water-based. Designed for applications with very high resistance to temperature. Very good performance in converting. Medium initial tack and peel adhesion.
Tack (N) stainless steel FTM-9: > 6
Cohesion (h) 1Kg FTM-8: > 6
Labelling temperature (°C): > 5
Usage temperature (°C): - 5 + 70

DRY TAC GTC 50/30

Additional information

The stated technical specification and information are of a general nature and are based on the experience and on the current knowledge of VISATAC wherefore the suitability of the product for the intended application and the end use cannot be guaranteed. The purchaser of the product is solely responsible to test and to approve the product under end use conditions, to determine the suitability for its purposes and to ensure the product meets the particular requirements. VISATAC cannot be held liable for unsuitable end use of their products. This product specification replaces all previous versions. All data is subject to change without prior notice.

Shelf life

1 year under generally recommended storage at a temperature between 20 °C and 25 °C and a relative humidity of 40-50 %