


(PATM0002)

BIO SILVER MIRROR 23 RV-1 GC60



- Metallised Compostible Film
- Coated 80
- Adhesive RV-1
- GC60

Facestocks

- **Reference 1:** Metallised Compostible Film
Characteristics:
Transparent cellulose film with metallised surface
Thickness (μ): 23
Grammage (gr/m²): 33
- **Reference 2:** Coated 80
Characteristics:
White coated, calendered, woodfree paper
Thickness (μ): 65
Grammage (gr/m²): 80

- **Adhesive**
Reference: RV-1
Characteristics:
Removable adhesive acrylic water-based.
Tack (N) stainless steel FTM-9: > 2
Cohesion (h) 1Kg FTM-8: > 3
Labelling temperature (°C): > 10
Usage temperature (°C): - 10 + 60

- **Liner**
Reference: GC60
Description:
Supercalendered glassine cream paper, one sided silicone coated.
Thickness (μ): 55
Grammage (gr/m²): 60

Additional information

The stated technical specification and information are of a general nature and are based on the experience and on the current knowledge of VISATAC wherefore the suitability of the product for the intended application and the end use cannot be guaranteed. The purchaser of the product is solely responsible to test and to approve the product as well as its printability under end use conditions, to determine the suitability for its purposes and to ensure the product meets the particular requirements. VISATAC cannot be held liable for unsuitable end use of their products. This product specification replaces all previous versions. All data is subject to change without prior notice.

Shelf life

1 year under generally recommended storage at a temperature between 20 °C and 25 °C and a relative humidity of 40-50 %