


(PASPM0009)

## VOID PET 50 WHITE GLOSS TC1 V-1 GW70



- VOID PET 50 White Gloss TC1
- Adhesive V-1
- GW70

### Facestock

Reference: VOID PET 50 White Gloss TC1

#### Characteristics:

White gloss polyester film, special treatment top coat TC1. If an attempt is made to remove the label, the lettering 'VOID' remains on the item.

Thickness ( $\mu$ ): 50

Grammage ( $\text{gr}/\text{m}^2$ ): 71

### Adhesive

Reference: V-1

#### Characteristics:

Permanent adhesive acrylic water-based. Designed for applications with very high resistance to temperature. Very good performance in converting. Medium initial tack and peel adhesion.

Tack (N) stainless steel FTM-9:  $> 6$

Cohesion (h) 1Kg FTM-8:  $> 6$

Labelling temperature ( $^{\circ}\text{C}$ ):  $> 5$

Usage temperature ( $^{\circ}\text{C}$ ):  $- 5 + 70$

### Liner

Reference: GW70

#### Description:

Supercalendered glassine white paper, one sided silicone coated

Thickness ( $\mu$ ): 62

Grammage ( $\text{gr}/\text{m}^2$ ): 72

### Additional information

The stated technical specification and information are of a general nature and are based on the experience and on the current knowledge of VISATAC wherefore the suitability of the product for the intended application and the end use cannot be guaranteed. The purchaser of the product is solely responsible to test and to approve the product as well as its printability under end use conditions, to determine the suitability for its purposes and to ensure the product meets the particular requirements. VISATAC cannot be held liable for unsuitable end use of their products. This product specification replaces all previous versions. All data is subject to change without prior notice.

### Shelf life

1 year under generally recommended storage at a temperature between  $20^{\circ}\text{C}$  and  $25^{\circ}\text{C}$  and a relative humidity of 40-50 %